

Solvable model for the standard folklore of the glassy state

Theo M. Nieuwenhuizen

*Department of Physics and Astronomy, University of Amsterdam
Valckenierstraat 65, 1018 XE Amsterdam, The Netherlands*

(Revised, September 28, 1999)

A model system with fast and slow processes is introduced. After integrating out the fast ones, the considered dynamics of the slow variables is exactly solvable. In statics the system undergoes a Kauzmann transition to a glassy state. The relaxation time obeys a generalized Vogel-Fulcher-Tammann-Hesse law. The aging dynamics on the approach to and below the Kauzmann temperature is analyzed; it has logarithmic behavior. The structure of the results could be general, as they satisfy laws of thermodynamics far from equilibrium. The original VFTH law is on the border-line between the regime where only the effective temperature of the slow modes is needed, and the regime where also an effective field occurs. The production rates of entropy and heat are calculated.

64.70.Pf, 75.10.Nr, 75.40.Cx, 75.50.Lk

Half a century ago Kauzmann pointed at the “entropy crisis” in glass forming liquids: The naive extrapolation of the entropy of an undercooled liquid goes below the entropy of the crystalline state, which is physically incorrect [1]. It is often assumed that a thermodynamic phase transition takes place around the “Kauzmann temperature” T_K , characterized by a vanishing configurational entropy. This prediction is very difficult to test experimentally, since the relaxation time may be very long. Experimental data for glass forming liquids are often fit to a Vogel-Fulcher-Tammann-Hesse (VFTH) [2] behavior $\tau_{eq} \sim \exp[A\gamma/(T - T_0)^\gamma]$. An entropic argument for the standard choice, $\gamma = 1$, was given by Adam and Gibbs [3]. A field-theoretic approach by Parisi [4] leads to $\gamma > 1$. These approaches share the commonly accepted point that T_0 and T_K coincide. In practice exponents $\gamma \neq 1$ are compatible with data; this merely affects the width of the fitting interval. Here we shall investigate universal aspects of this standard picture.

Very little is known about dynamics below the Kauzmann temperature. One simple, intriguing idea comes to the mind. Consider a glassy system that has aged a long time t . Can one say that all processes with equilibration time much less than t are in equilibrium, while the ones with timescale much larger than t are still quenched, leaving the processes with timescale of order t as the only interesting ones? Such an approach would be too naive for continuous phase transitions, where the timescale diverges algebraically at the critical point. However, in glasses there is an exponential divergence, and this might induce an asymptotic decoupling of the time-decades. Indeed, it occurs in the glassy regime of models with an Arrhenius (rather than VFTH) law, like the ferromagnetic Ising chain [5], harmonic oscillator and spherical spin models [6]. This asymptotic decoupling could be the basic ground for a generalization of equilibrium thermodynamics to systems far from equilibrium [6]. That approach involved systems where one extra variable was needed to describe the non-equilibrium physics, namely the effective temperature. In the present

work we shall encounter situations, where also an effective field is needed to describe the two observable quantities, energy and magnetization out of equilibrium. That case is of principle interest for glass forming liquids, as it was found experimentally that at given T, p the same volume can be reached via different histories. As they then lead to different futures, the glassy state of these systems cannot be coded using one extra variable [7].

In order to gain insight in properties of the standard picture, we introduce a simple model, with solvable dynamics. In the long time aging regime it leads to first order differential equations. We thus can study aging on the approach to and below the glass transition. Even though the physics of the model is quite simple, we shall set out to discover general aspects of the results by phrasing them in a thermodynamic language.

The model contains a set of N spins S_i , coupled to a slowly changing background field, that we model by a set of N harmonic oscillators x_i . All variables are only coupled locally, as is described by the Hamiltonian

$$\mathcal{H} = \frac{1}{2}K \sum_i x_i^2 - H \sum_i x_i - J \sum_i x_i S_i - L \sum_i S_i \quad (1)$$

The spins have no fixed length, but satisfy the spherical constraint $\sum_i S_i^2 = N$. In order to model the β -processes of a glass, we assume that the spins S_i move fast, and we shall consider only the time regime where they are at thermodynamic equilibrium. To model α -processes, we shall consider a dynamics where the x_i may fall out of equilibrium. Integrating out the S_i replaces the spin-part of the energy (1) by its free energy, which will act as an *effective* Hamiltonian for the slowly moving variables x_i ,

$$\mathcal{H}_{eff} = U - TS_{ep} \quad (2)$$

Here $U = Nu$ is the internal energy given by

$$u = \frac{U}{N} = \frac{1}{2}Km_2 - Hm_1 - w + \frac{T}{2}, \quad (3)$$

It depends on the two lowest moments of the x_i , $m_k = (1/N)M_k = (1/N)\sum_i x_i^k$, and w is the short hand

$$w = \sqrt{J^2 m_2 + 2JLm_1 + L^2 + \frac{1}{4}T^2}, \quad (4)$$

S_{ep} is the entropy of the equilibrium processes, i.e., of the spins,

$$S_{\text{ep}} = \frac{1}{2}N - \frac{1}{2}N \ln[\beta(w + \frac{1}{2}T)] \quad (5)$$

Being interested in the long-time aging behavior, we may restrict ourselves to the time-regime where the dynamics of the x_i can be described by a Monte Carlo dynamics. We must assume parallel updating, as sequential updating would not produce a long timescale in our system without two-particle interactions. We are thus considering a simple example of models typically studied numerically. Since it can even be solved analytically, we shall gain qualitative insight in the long time regime.

The rules for the MC dynamics are standard, and lead to evolution equations for $m_{1,2}$ that have the form

$$\dot{m}_1 = \int_{-\infty}^{\infty} dx y_1(x) p(x|m_{1,2}) W(\beta x) \quad (6)$$

$$\dot{m}_2 = 2 \int_{-\infty}^{\infty} dx \frac{x + \tilde{H} y_1(x)}{\tilde{K}} p(x|m_{1,2}) W(\beta x) \quad (7)$$

Let us explain how this comes about. For one MC step one shifts all x_i by an amount $r_i/\sqrt{N}$ with the r_i drawn from a symmetric Gaussian with variance Δ^2 . This updates $M'_{1,2} = M_{1,2} + \delta M_{1,2}$. According to the Metropolis algorithm, the move is accepted with probability $W(\beta x) = \exp(-\beta x)$ if the change in effective energy, $x = \mathcal{H}'_{\text{eff}} - \mathcal{H}_{\text{eff}}$, is positive; if x is negative the move is always accepted ($W(\beta x) = 1$). Such dynamical problems are well understood [8] [9]. The essential ingredient is the thermally averaged transition probability for a move characterized by x and δM_1 . It is the product of two factors: the first is a Gaussian in δM_1 with center $y_1(x)$ and width Δ_y ; the second factor, $p(x|m_{1,2})$ occurring in eqs. (6) and (7), is a Gaussian in x with center x_0 and width Δ_x . Defining $\mu_1 = \tilde{H}/\tilde{K} - m_1$ with

$$\tilde{H} = H + \frac{JL}{w + T/2}; \quad \tilde{K} = K - \frac{J^2}{w + T/2}, \quad (8)$$

the parameters of these Gaussians take the form

$$x_0 = \Delta^2 \tilde{K}/2, \quad \Delta_x = \Delta^2 \tilde{K} T_e, \quad (9)$$

$$y_1 = \beta_e \mu_1 (x_0 - x), \quad \Delta_y = \Delta^2 (1 - \beta_e \tilde{K} \mu_1^2). \quad (10)$$

Here $T_e = 1/\beta_e$ is a short hand for $T_e = \tilde{K}(m_2 - m_1^2)$; later we shall interpret it as an effective temperature.

We are still free to choose the variance Δ^2 of the Monte Carlo moves. To model glassy behavior we shall consider a dynamics that constrains the system's phase space to $m_2 - m_1^2 \geq m_0$ for some fixed m_0 . This mimics a glass that has no crystalline state, as occurs in atactic polymer melts. For some fixed m_0 and B , we thus let Δ depend on the instantaneous values of $m_{1,2}(t)$ according to

$$\Delta^2(t) = \frac{8T_e(t)}{\tilde{K}(t)} \Gamma(t) \quad (11)$$

where

$$\Gamma(t) \equiv \left(\frac{B}{\mu_2(t)} \right)^\gamma; \quad \mu_2(t) = m_2(t) - m_1^2(t) - m_0 \quad (12)$$

The power γ remains a free parameter, because we will not make a connection to an underlying microscopy.

The fact that Δ^2 becomes large near $\mu_2 = 0$ implies that there the trial moves are typically large, and thus unfavorable. Most of them will be rejected, implying, as shown below, a VFTH-type equilibrium relaxation time

$$\tau_{eq}(T) \sim \exp \Gamma_{eq} \sim \exp \left(\frac{A(T_0)}{T - T_0} \right)^\gamma \quad (13)$$

while $\tau_{eq} = \infty$ for $T < T_0$. Though the physics of our model (1) is simple, the choice (11), (12) for the timescale allows us to derive aspects of the long time aging regime below T_K , which could well be model independent.

Let us first look at the static regime, that has $\mu_1 = 0$. For large enough T , the variable μ_2 remains positive and the effective temperature is trivial: $T_e^{\text{eq}} = T$. A Kauzmann transition occurs at T_K set by $\mu_2 = 0$. Since states with $\mu_2 < 0$ cannot be reached, it is evident that the generally expected equality $T_0 = T_K$ holds. In statics μ_2 vanishes for all $T < T_0$, implying that T_e^{eq} follows from

$$\frac{Km_0 - T_e^{\text{eq}} + T}{Km_0 - T_e^{\text{eq}}} + \frac{D^2 m_0}{(JT_e^{\text{eq}})^2} = \frac{J^2 m_0}{(Km_0 - T_e^{\text{eq}})^2} \quad (14)$$

where $D = HJ + KL$. The Kauzmann temperature is the solution of $T_e^{\text{eq}}(T_0) = T_0$. Below T_0 , T_e^{eq} exceeds T , and it remains finite for $T \rightarrow 0$. All static observables can now be expressed in T_e^{eq} . Since $w = [J^2 m_0 + (DJ/T_e^{\text{eq}})^2 + T^2/4]^{1/2}$, we have the result for $m_1 = \tilde{H}/\tilde{K}$ via (8), and using $m_2 = m_1^2 + m_0$, we can find the energy from (3). Since $dT_e^{\text{eq}}/dT < 1$ at T_0^- , the specific heat makes an upward jump as function of T ; this happens also for $-\partial m_1/\partial T$. The very same features occur in the mean field glass model, the p -spin model, where $T_e^{\text{eq}} = x(T)/T$, with x the Parisi breakpoint [10].

We shall restrict ourselves to aging experiments at fixed T, H , where the system evolves from some initial state. An example is fast quenching from an equilibrium state at large temperature, for which initially $\mu_1 = 0$, $0 < \mu_2 \ll 1$. In the long time regime eqs. (6), (7) lead to first order differential equations for $\mu_{1,2}$

$$\dot{\mu}_1 = 4[aJrT_e - (1 + aD)(\Gamma + r)\mu_1]I \quad (15)$$

$$\dot{\mu}_2 = -8\left[\frac{rT_e}{\tilde{K}} - (\Gamma + r)\mu_1^2\right]I \quad (16)$$

where we denote $r = (T_e - T)/(2T_e - T)$, $I = \int dx p W$, and we introduce the shorthands

$$a = \frac{DJ^2}{\tilde{K}^3 w(w + T/2)^2}, \quad b = \frac{J^4 T_e}{2\tilde{K}^2 w(w + T/2)^2} \quad (17)$$

$\dot{\mu}_2$ in eq. (16) is dominated by the small factor $I \sim \exp(-\Gamma)$. This is the dynamic imprint of the static VFTH law (13), which may be more general. The solution follows readily, since the integral of an exponential is basically the same exponential. It is this property that leads to the asymptotic decoupling of decades, discussed in the introduction. In the aging regime one gets $t \sim t_0 \exp \Gamma$, equivalent to

$$\mu_2 = \frac{B}{[\ln(t/t_0)]^{1/\gamma}} \quad (18)$$

where t_0 depends logarithmically on t . Such logarithmic behavior is supposed to be the universal finger print for the glassy state; notice, however, that there can be a non-trivial exponent. For $T > T_0$ μ_2 will stick at $\mu_2^{\text{eq}} \sim T - T_0$, whereas for $T < T_0$ it will ultimately vanish.

To solve for $\mu_1(t)$ we divide eq. (15) by (16), which allows to express μ_1 in terms of μ_2 of eq. (18),

$$\frac{d\mu_1}{d\mu_2} = \frac{-aJ\tilde{K}rT_e + (1 + aD)(\Gamma + r)\tilde{K}\mu_1}{2rT_e - 2(\Gamma + r)\tilde{K}\mu_1^2} \quad (19)$$

There exist several ranges of solutions:

- Regime 0: $T > T_0$, all γ :

Here $r \sim T_e - T \sim \mu_2$. The solution is obtained by equating the numerator of the right hand side to zero,

$$\mu_1 = \frac{aJ\tilde{K}(1 + b)}{1 + aD} \frac{\mu_2}{\Gamma} \quad (20)$$

Since $\mu_1 \ll \mu_2$, it can be neglected to leading order.

- Regime 1: $T < T_0$, $\gamma > 1$:

As in Regime 0, but now r is of order unity,

$$\mu_1 = \frac{aJT_e}{1 + aD} \frac{r}{\Gamma} \quad (21)$$

Also in this case $\mu_1 \ll \mu_2$.

- Regime 2: $T < T_0$, $\gamma = 1$:

This is the case with a true VTFH-law. Quite surprisingly, eq. (19) exhibits several subregimes with different behavior: $\gamma = 1$ is the most difficult situation, too intricate to explain here in detail.

- Regime 3: $T < T_0$, $\gamma < 1$

Now the denominator of (19) becomes subleading, of order $\Gamma\mu_2 = B^\gamma\mu_2^{1-\gamma} \ll 1$, but it remains positive, thus assuring that μ_2 finally vanishes. It follows that

$$\mu_1 = \sqrt{\frac{rT_e}{\tilde{K}\Gamma}} \left(1 - \frac{(1 + aD)\tilde{K}}{2\gamma rT_e} \Gamma\mu_2\right) \sim \mu_2^{\gamma/2}, \quad (22)$$

so in this regime $\mu_2 \ll \mu_1$ can be neglected.

The magnetization approaches equilibrium as

$$m_1(t) = \frac{\tilde{H}^{\text{eq}}}{\tilde{K}^{\text{eq}}} - \frac{1}{1 + aD} \mu_1(t) - \frac{aJ\tilde{K}}{2(1 + aD)} \mu_2(t) \quad (23)$$

In regimes 0 and 1 its time-dependence is dominated by $\mu_2 \sim (\ln t)^{-1/\gamma}$, while in regime 3 the dominant term is $\mu_1 \sim (\ln t)^{-1/2}$. In all cases both $m_2 = m_0 + m_1^2 + \mu_2$ and the energy, see eq. (3), behave similar to m_1 .

It has long been a challenge to formulate glassy behavior in terms of the laws of thermodynamics, because that could point at universal behavior. Attempts to do so remained unfruitful till recently [7] [11]. In a recent series of papers we have shown that it can be done in model systems where only one extra variable, the effective temperature T_e , is needed to describe the physics [12] [5] [9]. The crucial step was to explain the paradoxes concerning the Ehrenfest relations and the Prigogine-Defay ratio [12]. In the present model there are two independent observables, $m_{1,2}(t)$ or, equivalently, $m_1(t)$ and $u(t)$. They result from the dynamics, but they can also be described by a thermodynamics at an effective temperature $T_e(t)$ and an effective field $H_e(t)$. To do so, let us calculate in a quasi-stationary approach the partition sum over macroscopically equivalent states

$$Z_e = \int Dx e^{-\beta_e [\mathcal{H}_{\text{eff}} + H M_1 - H_e M_1]} \delta(M_{1,2} - N m_{1,2}(t)) \quad (24)$$

By the extra terms in the exponent we eliminate H in favor of H_e . We find for the free energy $F = -T_e \ln Z_e$

$$F = U + (H - H_e)M_1 - TS_{\text{ep}} - T_e \mathcal{I} \quad (25)$$

where U and S_{ep} were defined in (3) and (5). The new term $\mathcal{I} = N[1 + \ln(m_2 - m_1^2)]/2$ is the entropy of the configurations with given $m_{1,2}$. Though our model is classical, we can impose $\mathcal{I} = 0$ at $T = 0$ by adding a constant, yielding $\mathcal{I} = (N/2) \ln(1 + \mu_2/m_0)$. In his seminal paper Kauzmann pointed out that the equilibrium configurational entropy vanishes already at T_K . We see that this is indeed the case here. We can also check another aspect of the standard folklore. Comparison with eq. (13) yields $\ln \tau_{\text{eq}} \sim (N/\mathcal{I})^\gamma$. This is the generalization of the Adam-Gibbs relation [3] to cases with $\gamma \neq 1$.

T_e and H_e are required to satisfy the saddle point equations that follow from varying $m_{1,2}$ in eq. (25), implying

$$T_e = \tilde{K}(m_2 - m_1^2) = \tilde{K}(m_0 + \mu_2) \quad (26)$$

$$H_e = K m_1 - \frac{J(J m_1 + L)}{w + T/2} = H - \tilde{K} \mu_1 \quad (27)$$

They only depend on H through $m_{1,2} = m_{1,2}(t; T, H)$.

In eqs. (9)-(11) it was already seen that the expression (26) for T_e was useful to shorten the dynamical equations. It can now be checked that $T_e - T_e^{\text{eq}} \sim +\mu_2 - \mu_1$, so it has no definite sign, whereas $H_e - H \sim -\mu_1$ is negative. It is now seen that the “simple” Regimes 0 and 1 have a natural interpretation: one then has $\mu_1 \ll \mu_2$, so the effective field $H_e \approx H$ is not needed: the glassy state is coded by the effective temperature alone. Such

a situation was encountered before in model glasses with $T_0 = 0$ [6] [9], and in the p -spin model [12] [13]. In the “complicated” Regimes 2 and 3 one ultimately has $T_e - T_e^{\text{eq}} \sim H_e - H$. Both parameters are thus needed to describe the evolution, a result that should be valid beyond our model. Systems with a true VFTH-law ($\gamma = 1$) are at the borderline, and thus more subtle.

We now consider which processes are involved at large time t . The change of energy may be cast in the form

$$\dot{u}(t) = -\frac{u(t)}{\tau(T, T_e(t))} \quad (28)$$

For $T > T_0$ the behavior $I \sim \exp(-\Gamma)$ reproduces at equilibrium eq. (13); Outside equilibrium it follows that $\tau(T, T_e) \approx \tau_{eq}(T_e)$, as was observed in systems with an Arrhenius law [6]. For $T < T_0$, $\gamma > 1$ (Regime 1) the timescale of a system characterized by T and T_e obeys a generalization of the VFTH-law

$$\tau(T, T_e) \sim \exp \Gamma = \exp \left(\frac{A(T)}{T_e - T_e^{\text{eq}}(T)} \right)^\gamma. \quad (29)$$

saying that the equilibrium VFTH law has a definite fingerprint on the aging dynamics below T_0 . Here, as well as in eq. (13), $A(T) = B\tilde{K}(1 + b/(1 + aD))$. In the cases $\gamma \leq 1$ there are various behaviors, that may not be universal. In all these cases it holds that for $t \gg t_0$ the active processes are indeed those with timescale $\tau(T, T_e(t)) \sim t$, as is consistent with the logarithmic time dependence: $u(t) = \tilde{u}(\ln t)$ implies $\dot{u} = -u/\tau \rightarrow \tau = (-u/\dot{u})t$.

Let us now consider the results from a more general thermodynamic point of view. The first law says that the change in energy is equal to the heat added to the system and the work done on the system, $dU = dQ - M_1 dH$. It is satisfied with

$$dQ = T dS_{\text{ep}} + T_e d\mathcal{I} + (H_e - H) dM_1 \quad (30)$$

This holds because of the presence of a free energy, eq. (25), satisfying $dF = -S_{\text{ep}} dT - \mathcal{I} dT_e - M_1 dH_e$. It does not invoke the relation between $m_1(t)$ and $m_2(t)$, which differs in the various regimes. The two entropic terms in (30) are related to the fast and slow processes, respectively [5] [12]. The last term is new; it results from irreversible internal work.

In the aging process the system will go to lower energy by producing heat at a rate $|dQ/dt|$, that follows from (30). It holds that $|dQ/dt| \sim |\dot{m}_1| + |\dot{m}_2|$. The dominant term is $\dot{S}_{\text{ep}} + \dot{\mathcal{I}} \sim \dot{m}_2$ in regimes 0 and 1, while it is solely due to $\dot{S}_{\text{ep}} \sim \dot{m}_1$ in regime 3.

In thermodynamics close to equilibrium a central role is played by the irreversible entropy production. For systems far from equilibrium, this is also the case. We now show that it can be derived explicitly for systems such as the present one. We write the change in total entropy $S = S_{\text{ep}} + \mathcal{I}$ as $dS = d_e S + d_i S$, where $d_e S = dQ/T$ is the externally supplied entropy, and $d_i S$ the internally produced entropy. This gives the general result

$$\frac{dS_i}{dt} = \frac{T - T_e}{T} \frac{d\mathcal{I}}{dt} + \frac{H - H_e}{T} \frac{dM_1}{dt} \quad (31)$$

It can be verified explicitly in our model that both contributions are non-negative, in accordance with the second law. The first term of (31) is of order $r\dot{m}_2$, and is dominant in regimes 0 and 1; The last term is of order $\mu_1|\dot{m}_1|$, and it dominates in regime 3.

In conclusion, we introduce an exactly solvable model glass with a set of fast variables (spherical spins) and a set of slow variables (harmonic oscillators). The fast modes are summed out. For the slow modes we assume a dynamics that obeys a generalized VFTH law, $\tau_{eq} \sim \exp A^\gamma(T - T_0)^{-\gamma}$. In statics there occurs a Kauzmann transition. We solve the aging dynamics, and verify a generalized Adam-Gibbs relation between the relaxation time and the configurational entropy. Below T_0 the relaxation time for a system described by its effective temperature may have a VFTH form, or a different one. The dynamically active processes have timescale $\sim t$.

The aging solution can be described by a quasi-static thermodynamic approach. Above the Kauzmann temperature T_0 one extra variable is needed, the effective temperature, that depends logarithmically on time. Below T_0 this persists in some cases, while in other cases also an effective field is needed. Systems with the original VFTH-law are at the borderline.

We finally derive the production rates of entropy and heat for systems described by an effective temperature and field. They are non-vanishing whenever the effective temperature deviates from the bath temperature, and/or when the effective field deviates from the external field.

We thank A. Allahverdyan, A. Crisanti, L. Leuzzi, L.S. Suttrop and G.H. Wegdam for discussion.

-
- [1] W. Kauzmann, Chem. Rev. **43** (1948) 219
 - [2] H. Vogel, Physik. Z. **22** (1921) 645; G.S. Fulcher, J. Am. Ceram. Soc. **8** (1925) 339; G. Tammann and G. Hesse, Z. Anorg. Allgem. Chem. **156** (1926) 245
 - [3] G. Adam and J.H. Gibbs, J. Chem. Phys. **43** (1965) 139
 - [4] G. Parisi, in *The Oscar Klein Centenary*, U. Lindström ed., (World Scientific, Singapore, 1995)
 - [5] Th.M. Nieuwenhuizen, J. Phys. A **31** (1998) L201
 - [6] Th.M. Nieuwenhuizen, Phys. Rev. Lett. **80** (1998) 5580
 - [7] G.B. McKenna, in *Comprehensive Polymer Science 2: Polymer Properties*, C. Booth and C. Price, eds. (Pergamon, Oxford, 1989), pp 311
 - [8] L.L. Bonilla, F.G. Padilla, and F. Ritort, Physica A **250** (1998) 315
 - [9] Th.M. Nieuwenhuizen, Phys. Rev. E, in press; cond-mat/9807161
 - [10] A. Crisanti and H.J. Sommers, Z. Phys. **B87** 341 (1992).
 - [11] C.A. Angell, Science **267** (1995) 1924
 - [12] Th.M. Nieuwenhuizen, Phys. Rev. Lett. **79**(1997) 1317
 - [13] J.A. Hertz, D. Sherrington, and Th.M. Nieuwenhuizen, Phys. Rev. E **60** (1999) 2460